



Product Definition:

Paste wax mix to improve washability and polishing of Pisa stuccos.

It can also be coloured using the Pisa Dye Toners or Universal Dyes, for achieving certain decorative effects such as: The "travertine" effect made using Medium Marmorino stucco for carrying out this decorative technique; other options are the Texturing Plaster superficial colouring, the encaustic painting effect also performed over the Marmorinos, etc.

Physical location: Indoors.

Technical Data:

PH: 7 ± 0.5

DENSITY: $0.8 \pm 0.05 \text{ g/cm}^3$

PRESENTATION VISCOSITY: Whitish paste that becomes clear when dry.

PACKAGING: 0.75 l tin = 640 g of product.

LIFE SPAN IN CONTAINER: Approximately 16 months in stable environmental conditions $+5^\circ\text{C}$ (min.) and $+32^\circ\text{C}$ (max.) without opening the tin. Avoid frost and high temperatures.

COLOURS: To obtain a mentioned decorative effect, it can be coloured with Pisa Dyes/Toners or Universal Tinctures without exceeding 0.5% by weight.

APPLICATION TOOLS: Brush, trowel, spatula, sponge.

Application conditions:

PREVIOUS PREPARATIONS: Surfaces must be dry, firm/set up, well adhered, free of salts, free of any biological contamination such as mould, algae, lichens, free of environmental contamination (grease stains, soot, substances of unknown nature, etc.); i.e., free of any visible or invisible substance or contaminant that prevents the perfect attachment and finish of the Stucco wax.

| Types of Surfaces | Application Method |
|--|---|
| Venetian Stuccoes | In paste as is, applied using a spatula or trowel and polished after at least 12 hours. |
| Marmorino Stucco | These stuccoes are not normally highly polished so it is best to use the wax diluted with 18% deodorised white spirit and applied with a well-extended cloth without polishing. |
| Texturing Plaster | Once the wax is coloured, spread it using a brush. |
| Medium Marmorino stucco "travertine effect". | Dilute the wax by 34%, stain it and apply it using a brush. It may be polished after 20 hours if desired. |
| Marmorino stuccoes with "encaustic finish". | Stain the wax as is and apply it using a trowel and/or spatula. |
| Woods | Apply several coats with a brush or rag and polish after 12 hours. |



For the proper polishing of our *Classic Venetian stucco and Venetian Lime*, the application system is as follows:

- 1) Extend the Stucco Wax on the covering made with stucco, using a coach builder spatula or a stainless steel trowel; paying special attention on not leaving "burrs" or thick wax sections, and using a tool in perfect conditions.
- 2) After approximately 12 hours, we will move on to the mechanical polishing.



1)



2)

WORKING TEMPERATURE OF BOTH THE ENVIRONMENT AND THE SURFACE: 7°C minimum and 32°C maximum

WASHABILITY: 7 days after the application under 20 °C at 55% relative humidity conditions.

THEORETICAL PERFORMANCE: depending on the product's roughness, planimetry and absorption.

| |
|--|
| 0,75 l = 24-26 m ² per coat |
|--|

CLEANING OF TOOLS: Water and soap.

PRECAUTIONS: None in particular, apply in well ventilated areas.